

DERBIBASE

Smooth Surfaced APP Modified Bitumen Base Sheet

ADVANTAGES

- ▶ **High quality** 2.0 mm (80 mil) smooth surfaced APP Modified Bitumen Roofing Membrane designed as a base or ply sheet
- ▶ Derbigum's **exclusive** blend of APP (atactic polypropylene) polymers and select asphalts enhances the weathering capabilities and UV resistance of the membrane.
- ▶ **Mid reinforced** with a heat resistant non-woven fiberglass mat that increases the membrane's strength and durability while still maintaining flexibility
- ▶ DERBIBASE is a completely **water-proof** base ply for field and flashings when side and end laps are heat welded.
- ▶ Product can also be applied with PERMASTIC Cold Adhesive or mechanically fastened.



TECHNICAL CHARACTERISTICS

CHARACTERISTIC	TESTED	ASTM Requirements Test Methods D6509		DERBIBASE Results*		UNITS
		MACHINE DIRECTION	CROSS DIRECTION	MACHINE DIRECTION	CROSS DIRECTION	
Tensile Strength	0 °F	70	70	142	132	lbf/in
	73 °F	50	50	70	64	lbf/in
Elongation	0 °F	1.0	1.0	3.0	3.0	%
	73 °F	1.0	1.0	3.0	3.0	%
Tear Resistance	73 °F	70	70	101	100	lbf
Dimensional Stability		1	1	0.05	0.05	%

CHARACTERISTIC	INITIAL	AGED	INITIAL	AGED	UNITS
Cold Flex	0	0	-24	-22	°C

Tested initially within 24 hours and again aged 28 days.

CHARACTERISTIC	MINIMUM	MINIMUM	UNITS
Compound Stability	275	300	°F
MIT	NA	5	%

* All values shown are nominal and subject to normal manufacturing tolerances.

PRODUCT INFORMATION

CHARACTERISTIC	U.S. CUSTOMARY	METRIC
Thickness	80 mil	2.0 mm
Length	66 ft 5 in	20.1 m
Width	39 3/8 in	1.0 m
Weight	94 lb	42.6 kg
Net Coverage	200 sq ft	18.6 sq m

ASTM Requirements Test Methods D6509

PACKAGING & STORAGE

Packaged 20 rolls per pallet. Rolls should be stored on end, on raised platforms protected from the weather.



4800 Blue Parkway, Kansas City, MO 64130 | PHONE: 800.727.9872 | FAX: 816.924.1542 | WEBSITE: www.derbigum.us | EMAIL: info@derbigum.us

SDS available
on request:
(800) 727-9872
www.derbigum.us

