

PRS GLASS PLY VI[®]

Fiberglass Ply Sheet

ADVANTAGES

- ▶ Premium fiberglass ply sheet with excellent tensile strength
- ▶ Meets or exceeds ASTM D2178-04 Type VI specifications
- ▶ Product carries an Underwriters Laboratories G2 classification
- ▶ Made from inorganic material that resists rotting
- ▶ Porosity of the felt allows for better asphalt penetration
- ▶ Can be applied using hot asphalt, PERMASTIC cold adhesive or mechanical fasteners



TECHNICAL CHARACTERISTICS

CHARACTERISTIC	TESTED	ASTM Requirements Test Methods D2178-04 Type VI		PRS Glass Ply VI Results*		UNITS
		MACHINE DIRECTION	CROSS DIRECTION	MACHINE DIRECTION	CROSS DIRECTION	
Tensile Strength	77°F	50	50	60	60	lbf/in

* All values shown are nominal and subject to normal manufacturing tolerances.

PRODUCT INFORMATION

CHARACTERISTIC	U.S. CUSTOMARY	METRIC
Length	180 ft	54.9 m
Width	36 in	0.9 m
Weight	49.5 lb	22.2 kg
Net Coverage	487 sq ft	45.2 sq m

PACKAGING & STORAGE

Packaged 20 rolls per pallet. Rolls should be stored on end, on raised platforms protected from the weather



SDS available
on request:
(800) 727-9872
www.derbigum.us

